



Application Note AN-NIR-102

用近外光法量聚的密度

Simple routine analysis of polymer pellets

Aside from melt flow rate, density is the most important parameter to describe the properties of polyethylene (PE) materials. PE stiffness, rigidity, and heat resistance increase with higher density. Various testing methods exist for density in PE – the most common is by density balance, measuring the buoyancy in a liquid (ASTM D792). This test is easy to perform, but the method contains a variety of measurement errors sources, such as specimen fixation

corrections, temperature changes, or air bubbles within the sample pellets.

Trapped air bubbles formed during polymer pellet production result in lower density values when measured with the buoyancy method. In contrast, near-infrared spectroscopy (NIRS) is a fast analytical technique which shows a low influence on density measurement error if any air bubbles are present in the sample material.

29 different polyethylene samples with varying density were measured on the Metrohm NIRS DS2500 Solid Analyzer (**Figure 1**) as well as with the buoyancy method described in ASTM D792. All measurements on the DS2500 Solid Analyzer were performed in rotation to average the subsample

spectra. This setup with the DS2500 large sample cup reduces influences from the particle size distribution of the polymer pellets. Data acquisition and prediction model development were performed with the software package Vision Air Complete.

Table 1. Hardware and software equipment overview.

Equipment	Metrohm number
DS2500 Solid Analyzer	2.922.0010
DS2500 large sample cup	6.7402.050
Vision Air 2.0 Complete	6.6072.208



Figure 1. Metrohm NIRSDS2500 Solid Analyzer used for determination of density in PE pellets.

RESULT

The obtained Vis-NIR spectra (Figure 2) were used to create a prediction model for the density value determination in PE pellets. To verify the quality of the prediction model, correlation diagrams were

created which display the correlation between the Vis-NIR prediction and primary method values received from the supplier (**Figures 3–4**).




Figure 2.

RESULT DENSITY IN PE




Figure 3.

Figures of Merit	Value
R^2	0.979
Standard Error of Calibration	2.48 kg/m ³
Standard Error of Cross-Validation	3.42 kg/m ³

RESULT DENSITY IN PE




Figure 4.

Figures of Merit	Value
R ²	0.948
Standard Error of Calibration	3.95 kg/m ³
Standard Error of Cross-Validation	6.00 kg/m ³

RESULT DENSITY IN PE

In addition to the NIRS analysis, the density of the pellets was measured with the density balance in the laboratory. These results deviated even more from the reference values of the supplier, compared to the NIRS results (**Table 2**). This can be explained due to the appearance of air bubbles in some of the polymer pellets, visible in the CT scan displayed in **Figure 5**. The respective figures of merit (FOM) of the NIRS analysis related to the reference data from the polymer production facility is displayed in **Figure 3**. The correlation of the density balance measurements performed in the lab with the predicted NIRS analysis is displayed in **Figure 4**.




Figure 5. Example of computer tomography (CT) scan of polyethylene pellets showing air bubbles inside the polymer granulate.

CONCLUSION

This Application Note shows the feasibility of NIR spectroscopy for the analysis of density in polyethylene granulates. Compared to the standard method (**Table 2**), NIRS analysis shows

a lower prediction error when air bubbles are present in polymer pellets. In addition, sample handling with near-infrared spectroscopy is easier to perform and therefore less error-prone.

Table 2. Comparison of density prediction with NIRS and density balance according to ASTM D792.

	Density: producer	Density: lab balance	Density: NIRS	Air bubbles present
Sample 1	953 kg/m ³	941 kg/m ³	952 kg/m ³	Yes
Sample 2	950 kg/m ³	935 kg/m ³	953 kg/m ³	Yes
Sample 3	918 kg/m ³	917 kg/m ³	915 kg/m ³	No

CONTACT

瑞士万通中国
北京市海淀区上地路1号院
1号楼7702
100085 北京

marketing@metrohm.com.cn

CONFIGURATION



DS2500 Solid Analyzer

固的近外光,用于生境和室中的量。

DS2500 分析是的活解决方案,用于整个生程中的固体、乳膏和液体行常分析。其固的使 DS2500 Analyzer 分析不受灰、湿度、振和温度波的影,因此非常用于在劣的生境中使用。

DS2500 涵盖了从 400 到 2500 nm 的整个光范,并能在不到一分内提供准和可再的果。DS2500 Analyzer 足制行的要求,并由于操作便而能助用完成其日常工作任。

由于与匹配,附件可以承受任何具有挑性的品型,例如:粒料之的粗粒固体或乳膏之的半固体品,可得果。量固体的候,使用 MultiSample Cup 可以提高生率,可以自批量量多 9 个品。



DS2500

用于在不同品位置使用 NIRS DS2500 Analyzer 采集粉末和粒反射光的大号品容器。